

TRUPOTAN[®] CFP

Tanning and retanning for all types of leathers.

| | |
|---------------------------|------------------------------------|
| Basis: | Polymer - diphenyl sulfone syntan. |
| Appearance: | amber liquid |
| Active matter: | approx. 38 % |
| pH value (1 : 10): | approx. 4 |

Properties:

TRUPOTAN CFP is a syntan designed to be used on all types of leathers and articles, both in the tanning and retanning stages.

TRUPOTAN CFP provides extremely white leathers, therefore it will be an excellent choice in the production of white or pastel shades.

TRUPOTAN CFP provides very soft leathers with excellent fullness and round handle.

TRUPOTAN CFP has very good light fastness and heat yellowing.

TRUPOTAN CFP is the recommended syntan in the production of leathers with very low values of free formadehyde.

TRUPOTAN CFP can be used in the pre-tanning of chrome free articles on all types leathers. Used alone in sheepskins it's possible to obtain values of TG around 80°C

TRUPOTAN CFP as a retanning agent provides very soft milled leathers with fine and regular grain.

Application:

As a retanning agent for bovine on WB or WW: 5% - 15% on shaved weight.

As a retanning agent for sheepskins: 6% - 10% on shaved weight.

As a single pre-tanning agent or in combination with others: 10% - 20% on shaved weight.

As a retanning agent for chrome free upholstery leather: 10% - 20% on shaved weight in combination with vegetable extracts or other syntans.

Safety and storage:

When handling **TRUPOTAN CFP**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN CFP can be stored for up to 24 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN CFP** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

05/2014

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPOTAN: registered trademark of TRUMPLER