

SOLVOTAN XS

Cationic Fatliquor

Basis:	Cationic fatliquor
Appearance:	White paste
Charge:	Cationic
Active matter:	Approx. 48 %
10%pH EMULSION	Approx. 5,5
Acid stability:	Good
Hard water stability:	Good
Chrome stability:	Good

Properties:

SOLVOTAN XS gives a silky handle as well as writing effects without showing superficial over fatliquoring.

SOLVOTAN XS is used in the production of suede leathers showing even and intensive dyeings.

Application:

The leather is fatliquored before tanning with 1-2 % **SOLVOTAN XS** dissolved in 3 times its weight of water at 50°C. This results in clean tannings, good grain lubrication with a better chrome distribution.

Suede for shoes

% on dry weight

1.000 % Water at a 50°C.

3-5 % SOLVOTAN XS

Run 15-20 minutes

Top for shoe upper

% on shaved weight

150 % Water at 50°C.

1-2 % SOLVOTAN XS

0,5 % TRUPON PBE

Safety and storage:

When handling **SOLVOTAN XS**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details, please refer to our safety data sheets.

SOLVOTAN XS can be stored for up to 18 months, if temperatures below 5°C and above 40°C can be avoided.

On prolonged storage the product may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

09/2016

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

SOLVOTAN: registered trademarks of TRUMPLER