

# TRUPON<sup>®</sup> DB-80

<b>Basis:</b>	Combination of phospholipids and synthetic raw materials
<b>Appearance:</b>	Brown viscous oil
<b>Charge:</b>	Anionic
<b>pH value(1 : 10):</b>	approx. 7.3
<b>Active substance::</b>	approx. 80 %
<b>Acid stability:</b>	Good
<b>Chrome stability:</b>	Good
<b>Hard water stability:</b>	Good
<b>Light fastness:</b>	Good
<b>Heat yellowing:</b>	Good

## Properties:

**TRUPON DB-80** produces exceptional softness on clothing leather for both sheep and cow, coupled with a waxy, slightly wet handle.

**TRUPON DB-80** will enhance the colour value of dyed leather.

When used on upholstery leather, **TRUPON DB-80** will improve tensile strength and the flame resistance.

## Applications:

On suede leathers, **TRUPON DB-80** exhibits excellent softness together with outstanding sheen and lustre.

Thanks to its good chrome stability, **TRUPON DB-80** could be used (previously dissolved) in chrome tanning baths or retanning baths with chrome and **TRUPOTAN EH**.

**TRUPON DB-80** can be used alone or in combination with other anionic fatliquors depending upon the type of leather required.

**TRUPON DB-80** should be prepared for use by adding it to a minimum of five times its own volume of water at 50 °C whilst stirring.

## Safety and storage:

When handling **TRUPON DB-80** normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPON DB-80** can be stored for up to 18 , if temperatures below 5 °C and above 40 °C can be avoided.

07/2018

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

TRUPON: registered trademark of TRUMPLER